Wolf Gordon 1




Image depicts 12x12 inch section.

© 2024 Wolf-Gordon Inc. All Rights Reserved

Marlowe HARBOR

Category: Upholstery
Material: Polycarbonate
Physical Properties

Content: 100% Polyurethane

Backing: Polyester Knit

Width: 54"

Weight: 25.00 oz per linear yards

Performance

Flame Resistance: Passes Cal TB 117-2013, AB 2998 compliant - Passes NFPA 260/UFAC

Wet and Dry Crocking: Passes AATCC 8 - Dry: Grade 5; Wet: Grade 5

Breaking Strength: ASTM D751 - Warp: 121 lbs; Weft: 137 lbs

Marine Applications: IMO FTP Code 2010 Abrasion: 100,000* double rubs, Wyzenbeek

Coating Adhesion: ASTM D751 - Warp: 13.6 lbs; Weft: 12.0 lbs

Tear Strength: ASTM D2261 - Warp: 8.5 lbs; Weft: 8.2 lbs Seam Strength: ASTM D751- Warp: 72.7 lbs; Weft: 97.8 lbs

Colorfastness to Light: Passes AATCC 16 - Grade 4 @ 200 hours

Cleaning Code: W-S = Clean with either a water- or solvent-based

agent; a diluted bleach solution can be used Hydrolysis Resistance: ISO 1419 - 15 weeks

Sustainability

Free of conflict minerals, heavy metals, PFC/PFOA/PFOS

Printed with solvent-free inks

^{*}Actual Wyzenbeek test results: 200,000 double rubs without showing wear. Please note that actual Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.